

# PHYSICAL TECHNIQUES FOR DETERMINING THE RESISTANCE TO HEAT TRANSFER PROVIDED BY CLOTHING

Elizabeth A. McCullough  
Institute for Environmental Research  
Kansas State University  
Manhattan, Kansas, USA

It is necessary to quantify the thermal insulation and evaporative resistance properties of clothing systems so that the heat exchange between the body and the environment can be determined and a person's performance in that environment can be predicted using biophysical models. This paper reviews the physical methods for directly measuring resistance data on fabrics and clothing ensembles and discusses problems associated with different techniques. In addition, methods for estimating the resistance values for clothing from different fabric and clothing properties will be mentioned.

## FABRICS

The resistance to dry heat transfer (i.e., insulation) can be measured using the rate of cooling method, the constant temperature method (e.g., guarded hot plate), and heat flow meter. Flat plate instruments or cylinders have been used, with each type having advantages and disadvantages over the other. Fabric insulation can be estimated from thickness, so the compressometer, micrometer, and pendulum methods will be discussed. The evaporative resistance of fabrics can be measured using a sweating hot plate device or cylinder. A liquid barrier of known resistance is needed to keep the fabric dry during the test. Measurements can be made with and without a temperature gradient between the hot body and the environment. Other methods for measuring the diffusion of water vapor through a fabric include the ASTM control dish method and the Canadian DND apparatus. [1-10]

## CLOTHING TESTS

Thermal manikins are constant temperature methods for measuring the insulation values of clothing ensembles. They take into account several variables that affect heat transfer from the body (i.e., the amount of body surface area covered by clothing, the distribution of the insulation over the body, the looseness or tightness of fit, and the increased surface area for heat loss. Manikins can be divided into body segments with independent temperature control and measurement or consist of one circuit. They can be made to sweat externally by using a cotton knit skin saturated with water, but this test is a transient one. Efforts to develop manikins with steady-state sweating capability are still underway. Manikins also can be attached to auxiliary motion systems so that clothing ventilation can be studied. [11-20]

## DYNAMIC VS. STEADY-STATE TESTS

These test methods have been criticized because they are conducted under steady-state conditions whereas, a person wearing clothing is moving around--changing body position, movements, and environments. Thus, quantifying the thermal responses of clothing to transient conditions is important. A thermal manikin can be used to quantify the changes in insulation due to temperature and humidity transients by moving the manikin from one environment to another, or by changing the environment around him. A manikin can be used to quantify the effect of body position and motion on the insulation value of the clothing also. Unfortunately, these tests have not been conducted with the manikin sweating, so changes in evaporative heat transfer must be estimated from fabric and clothing data. [21]

## REFERENCES

1. Kamata, Y., Kato, T., Azumi, H., and Watanabe, S., Convective heat transfer from human body (Part 1. A simulation by vertical cylinder). *Sen-i Gakkaishi*, 42(3): 57-63, 1986.
2. ASTM. 1989 Annual Book of Standards. Philadelphia, PA: American Society for Testing and Materials, 1989.
3. Fonseca, G. F. and Breckenridge, J. R., Wind penetration through fabric systems--Part 1. *Textile Research Journal*, 35(2): 95-103, 1965.
4. Takeuchi, M., Isshiki, N., and Ishibashi, Y., Heat transfer on cylinder covered with close-fitting fabrics (Part I, Wind penetration through fabrics). *Bulletin of the JSME*, 25(207): 1406-1411, 1982.

5. Woodcock, A. H., Moisture transfer in textile systems. *Textile Research Journal*, 32: 622-633, 1962.
6. Dolhan, P. A., A comparison of apparatus used to measure water vapour resistance. *Journal of Coated Fabrics*, 17(10): 96-109, 1987.
7. Farnworth, B. and Dolhan, P. A., Apparatus to measure the water vapour resistance of textiles. *Journal of the Textile Institute*, 75: 142-145, 1984.
8. Meinander, H., Measurements of wet heat transmission through textile materials. *Proceedings of the International Conference on Biophysical and Physiological Evaluation of Protective Clothing*. Lyon, France, 1983.
9. Whelan, M. E., MacHattie, L. E., Goodings, A. C., and Turl, L. H., Part III: The resistance of fabrics to the passage of water vapor by diffusion. *Textile Research Journal*, 25(3): 211-223, 1955.
10. Morris, G. J., Thermal properties of textile materials. *Journal of the Textile Institute*, 44: T449-476, 1953.
11. Wyon, David P., Use of thermal manikins in environmental ergonomics. *Scand. J. Work Environ. Health*, 15(suppl. 1): 84-94, 1989.
12. McCullough, E. A., Jones, B. W., and Huck, J., A comprehensive data base for estimating clothing insulation. *ASHRAE Transactions*, 91(2): 29-47, 1985.
13. McCullough, E. A., Jones, B. W., and Tamura, T., A data base for determining the evaporative resistance of clothing. *ASHRAE Transactions*, 95(2): 1989.
14. Lotens, W. A. and Havenith, G., Calculation of clothing insulation and vapour resistance, TNO Institute for Perception. Soesterberg, The Netherlands, pp 5-33, 1989.
15. Umbach, K. H., Physiological tests and evaluation models for the optimization of the performance of protective clothing. In *Environmental Ergonomics*, edited by I. B. Mekjavic, E. W. Banister, and J. B. Morrison, pp 139-176, Philadelphia, Taylor & Francis Ltd, 1988.
16. Oohori, T., Berglund, L. G., and Gagge, A. P., Simple relationships among current vapour permeability indices of clothing with a trapped-air layer. In *Environmental Ergonomics*, edited by I. B. Mekjavic, E. W. Banister, and J. B. Morrison, pp 177-183, Philadelphia, Taylor & Francis Ltd, 1988.
17. Olesen, B. W., Hasebe, Y., and de Dear, R. J., Clothing insulation asymmetry and thermal comfort. *ASHRAE Transactions*, 94(1): 1988.
18. Fonseca, G. F., Sectional dry-heat-transfer properties of clothing in wind. *Textile Research Journal*, 45(1): 30-34, 1975.
19. Olesen, B. W., Sliwinska, E., Madsen, T. L., and Fanger, P. O., Effect of body posture and activity on the thermal insulation of clothing: measurements by a movable thermal manikin. *ASHRAE Transactions*, 88(2): 791-805, 1982.
20. Mecheels, J. and Umbach, K. H., Thermophysiological properties of clothing systems. *Melliand Textilberichte (English ed.)* (2): 1977.
21. de Dear, R. J., Knudsen, H. N., Pejtersen, J., Ring, J. W., Li, T. L., Puntener, T. W., Tanabe, S., Mackeprang, J., and Fanger, P. O., Impact of air humidity on thermal comfort during step-changes. *ASHRAE Report 503*, Technical University of Denmark, 1988.